

# Trend HS P

## Plastomeric polymer distilled bitumen waterproofing membrane



**TREND HS P** is a prefabricated PLASTOMERIC (APP) waterproofing membrane offering good performance.

Made from a polymer-modified distilled bitumen compound.

**TREND HS P** has a polyester nonwoven carrier stabilized with glass strands parallel to the machine direction. The carrier gives tensile strength in all directions, as well as good puncture resistance and dimensional stability.

**Flexibility at low temperature**  
-5 °C

**CE** 1370 PRODUCT COMPLIANT WITH EUROPEAN STANDARD

**CSI** WATER VAPOUR TRANSMISSION PROPERTIES

### INTENDED USE

PRODUCT	EN 13707 ROOFS						EN 13969 FOUNDATIONS			EN 13859-1 UNDERLAY FOR DISCONTINUOUS ROOFING	EN 13970 VAPOUR BARRIER	EN 14695 BRIDGES AND VIADUCTS
	SINGLE-PLY		MULTI-PLY				ROOT BARRIER	RISING DAMP	GROUNDWATER			
	EXPOSED	BALLASTED	EXPOSED		BALLASTED							
				BASE LAYER	CAP SHEET	BASE LAYER	CAP SHEET					
TREND HS P 4,5 kg GF					•						•	

TREND HS P can be applied as part of a MULTI-PLY ROOF, in EXPOSED waterproofing systems. The membrane can be applied as a CAP SHEET.

### FINISHES

The **TREND HS P** membrane is supplied in a standard version with a mineral surface and is covered with flakes of natural or colored ceramic slate of variable size. The mineral-surfaced version may undergo variations in colour tones due to time and shelf life. It must be considered a natural phenomenon that, after application, the exposure to atmospheric agents will tend to uniform the colour within a few months.

The underside comes with a standard protective finish consisting in a heat-fusible polyethylene film.

For further information on other available finishes, please contact the Polyglass SpA Sales Department.

#### Top finishes



Chippings (G)

#### Bottom finishes



Heat-fusible polyethylene film (F)

### AVAILABLE COLOURS

Slate chippings in a choice of:



Grey



Green



Red



White



\* Reflect White

\* Highly reflective colours (Cool Roof).

Reflect White - SRI (Solar Reflectance Index) ASTM E 1980-11: 57%<sup>1</sup>; R: 48%; E: 94%.

<sup>1</sup> Initial values according to ASTM, referring to new materials.

## TECHNICAL CHARACTERISTICS

STANDARD	TECHNICAL CHARACTERISTICS	UNIT OF MEASURE	TREND HS P G
EN 1848-1	WIDTH	m	≥ 1
EN 1848-1	LENGTH	m	10 (±1%)
EN 1849-1	THICKNESS	mm	NPD
EN 1849-1	AREA MASS	kg/m <sup>2</sup>	4,5 (±10%)
EN 1848-1	STRAIGHTNESS	mm/10 m	Meets the requirements
EN 1928-B	WATERTIGHTNESS	kPa	Meets the requirements
EN 1931	WATER VAPOUR RESISTANCE FACTOR $\mu$	-	60000 (±20%)
EN 13897	WATERTIGHTNESS AFTER STRETCHING AT LOW TEMPERATURE	kPa	NPD
EN 13501-1	REACTION TO FIRE	Class	E
EN 13501-5	EXTERNAL FIRE PERFORMANCE	Class	NPD
EN 12039	ADHESION OF GRANULES	%	≤ 30
EN 1850-1	VISIBLE DEFECTS	-	None
EN 1107-1	DIMENSIONAL STABILITY	%	≤ 0,3
EN 12316-1	PEEL RESISTANCE	N/50 mm	NPD
EN 12317-1	SHEAR RESISTANCE Longitudinal Transversal	N/50 mm N/50 mm	NPD NPD
EN 12691-A	RESISTANCE TO IMPACT (RIGID SUPPORT)	mm	≥ 400
EN 12691-B	RESISTANCE TO IMPACT (SOFT SUPPORT)	mm	≥ 500
EN 12730-A	RESISTANCE TO STATIC LOADING (SOFT SUPPORT)	kg	≥ 10
EN 12730-B	RESISTANCE TO STATIC LOADING (RIGID SUPPORT)	kg	≥ 15
EN 12310-1	RESISTANCE TO TEARING Longitudinal Transversal	N N	130 (±30%) 130 (±30%)
EN 12311-1	TENSILE STRENGTH Longitudinal Transversal	N/50 mm N/50 mm	400 (±20%) 300 (±20%)
EN 12311-1	ELONGATION AT BREAK Longitudinal Transversal	% %	35 (±15) 30 (±15)
ASTM D 1000	PEELING	N/10 mm	NPD
EN 1109	COLD FLEXIBILITY	°C	≤ -5
EN 1110	FLOW RESISTANCE AT ELEVATED TEMPERATURE	°C	≥ 110
<b>DURABILITY AFTER AGEING</b>			
EN 1931 - EN 1296	WATER VAPOUR RESISTANCE FACTOR AFTER THERMAL AGEING $\mu$	-	± 50% initial value
EN 1931 - EN 1847	WATER VAPOUR RESISTANCE FACTOR AFTER EXPOSURE TO CHEMICAL AGENTS $\mu$	-	± 50% initial value
EN 1928-B - EN 1296	WATERTIGHTNESS AGAINST ARTIFICIAL AGEING	kPa	Meets the requirements
EN 1928-B - EN 1247	WATERTIGHTNESS AGAINST CHEMICAL	kPa	Meets the requirements
EN 1850-1 - EN 1297	ARTIFICIAL AGEING BY LONG TERM EXPOSURE TO THE COMBINATION OF UV RADIATION, ELEVATED TEMPERATURE AND WATER	-	Meets the requirements
EN 1109 - EN 1296	ARTIFICIAL AGEING BEHAVIOUR (COLD FLEXIBILITY)	°C	NPD
EN 1110 - EN 1296	ARTIFICIAL AGEING BEHAVIOUR (FLOW RESISTANCE)	°C	≥ 100
<b>ADDITIONAL DATA</b>			
EN 13583:2012	DETERMINATION OF HAIL RESISTANCE	m/s	NPD
-	DETERMINATION OF HAIL RESISTANCE - VKP APIB N° 09	Class	NPD
SP METHOD 3873	PERMEABILITY TO RADON GAS	-	NPD
SP METHOD 3873	TRANSMITTANCE TO RADON GAS	-	NPD
BR 2012	TRANSMITTANCE TO METHANE GAS	-	NPD
IEC 62631-3-1:2016	VOLUMETRIC RESISTIVITY	$\Omega$ cm	NPD
EN 13948	RESISTANCE TO ROOT PENETRATION	-	NPD
-	THERMAL CONDUCTIVITY	W/mK	0,20
-	THERMAL CAPACITY	kJ/K	1,20

## PACKAGING

PRODUCT	THICKNESS mm	WEIGHT kg/m <sup>2</sup>	DIMENSIONS m
TREND HS P G F	-	4,5	1x10

## STORAGE

The product comes in rolls and is packed upright on shrink-wrapped pallets.

Use always a weight distributing element if you are forced to stack the pallets one on top of each other. A solid distributing element will avoid damages to the rolls underneath. Contact with solvents or organic liquids can damage the product.

Keep the product in a dry place, out of direct sunlight, protected from heat sources and freezing temperatures.

# Trend HS P

## INSTALLATION TIPS

The surface of any substrate due to be covered with **TREND HS P** must be flat, dry, clean, and free of all foreign matter or loose material.

When laying over old waterproofing build-ups (refurbishment work), the old system and its individual layers must be checked to ensure they are still properly adhered to the substrate.

Excessive moisture levels on the surfaces to be waterproofed can result in membranes coming off. If applied on top of insulating layers, said insulation must always be applied on top of a suitable vapour barrier; the individual insulation board must be glued on or fixed mechanically to the substrate.

Before applying the membranes, coat the substrate with an adhesion-promoting primer: either solvent-based products such as POLYPRIMER and POLYPRIMER HP or water-based product such as IDROPRIMER.

Fully-adhered application is generally the norm and involves lightly torching with a propane gas torch, following the instructions given on the intended use chart. During the membrane's installation, be careful not to puncture the surface in any way that is likely to damage the membrane's surface (footwear with spikes or studs, leaving anything pointed or with a small surface area sitting on top, sharp objects, etc.).

When applied as an exposed layer, the membrane with the smooth surface finish must be protected - at least 3 months after application and, whatever the case, waiting until it has had time to oxidize - with protective and/or reflective paints from the SPECIAL PRODUCTS line.

Mineral-surfaced membranes are naturally subjected to lose slate granules during handling and installation operations. It is also advisable to pay attention to the works following the installation of the product.

For further details on application, please contact the Polyglass SpA Technical Support Department.

## SAFETY RULES

The polymer bitumen membranes, manufactured by Polyglass SpA, are made from bitumen distilled from crude oil and do not contain tar (derived from coal), asbestos or chlorine.

## LEGAL RULES

The values given are approximate average data relating to the current product range and may be edited or updated by Polyglass SpA at any time without any prior notice. As Customer or User, it is your responsibility to check that the technical data sheet you have is valid for the batch of product in your hands and, whatever the case, that you have the latest version issued.

Always refer to the latest up-to-date version of the Technical Data Sheet and relevant Declaration of Performance, both of which you can find on our site [www.polyglass.com](http://www.polyglass.com). As the End User, it is your responsibility to check that the product is fit for its intended purpose.

PRODUCT FOR PROFESSIONAL USE.

